













Type L-MDF according to EN 622-5

### Scope

High quality light weight no added formaldehyde resin (NAF) MDF board for non load-bearing applications in dry conditions.

#### **Description**

MDF board with a hard, fine and smoothly sanded surface, characterised by extremely low formaldehyde emission.

MDF Fibrabel® Pure is approved (n° N-14-177) by the by Air Resource Board (ARB) as a no-added formaldehyde based resin (NAF) MDF board (section 93120.3 of the ATCM 'Airborne Toxic Control Measure'), This implies that formaldehyde emission is less than 0,04 ppm (90% of tested material), with a maximum of 0.06 ppm for every single measurement.

Moreover, MDF Fibrabel® Pure holds the German 'Der Blaue Engel' certificate for thickness 12 – 25 mm, and is classified as F\*\*\*\* according JIS A 1460, for thickness 9 – 30 mm.

Upon request, this MDF board can be supplied with PEFC, FSC or FSC Controlled Wood certificate.

## **Use of the product**

MDF Fibrabel® Pure is suitable for interior decoration, industrial processing and furniture production. The board can be lacquered or finished with paper, foil, melamine, veneer or high pressure laminate.

The board must be applied in service class 1 (restrictions in temperature and ambient humidity) and can only be used in biological hazard class 1 of EN 335-3. The boards must be protected from any direct contact with water. They must be stacked flat, on a pallet or using a sufficient number of cross members. Boards should not be stored vertically, unless ground contact can be avoided. The board will expand or shrink under variable humidity conditions. Use suitable sawing, milling and drilling tools.















#### **Dimensions**

Thickness: 9 to 40 mm. Maximum width 255 cm. Maximum length 630 cm. Standard thicknesses and dimensions are listed in our stock program. Furthermore, Spanolux has high-capacity saws that support all sawing dimensions. In principle, all thicknesses and lengths/widths are available within the press capabilities.

Contact our sales team or send an e-mail to sales.spanolux@unilin.com for further details.

# **Technical specifications**

Property	Test method	Unit	Ranges of nominal thickness (mm)				
			> 6 to 9	> 9 to 12	> 12 to 19	> 19 to 30	> 30 to 45
Swelling in thickness 24 h	EN 317	%	20	16	14	12	11
Internal bond	EN 319	N/mm <sup>2</sup>	0,45	0,45	0,45	0,45	0,40
Bending strength	EN 310	N/mm <sup>2</sup>	20	20	18	15	14
Modulus of elasticity in bending	EN 310	N/mm <sup>2</sup>	1700	1700	1600	1500	1400



Spanolux SPRL - Rue de la Forêt 2 - B-6690 Vielsalm T +32 80 29 27 10 - F +32 80 29 27 23 sales.spanolux@unilin.com - TVA BE 0456 573 456

The data on this information sheet are based on internal testing and are purely informative and are provided according to Spanolux SPRL knowledge at the time it was issued. Nothing in this information sheet can be construed as a commitment of Spanolux SPRL, nor can it result in any liability whatsoever of Spanolux SPRL. The information provided is subject of change at any time without any prior notification. © Spanolux - all rights reserved

